# PVC Vinyl Strip Door 4/25 In. Standard Overlap Header Mount 96 In. x 96 In. Clear

**MODEL TG-1600-S-H-96-96**

Loading Dock Equipment / Vinyl Strip Doors

## PRODUCT OVERVIEW

Vinyl strip doors help control noise, dust, fumes, and smoke while minimizing drafts, reducing illnesses, and accidents. The strip doors offer visual clarity without sacrificing safety. The material design also deters UV rays during direct sunlight when applied to load docks and external doorways . The simple low cost design is easy to maintain. Standard material design meets USDA requirements and is great for refrigeration applications up to -10 degrees Fahrenheit. All doors are shipped pre-assembled and ready for installation. Installation hardware not included. Custom door sizes and material available, contact factory.

## KEY FEATURES

- Vinyl strip design helps to minimize heating and cooling costs
- Clear strips offer visual clarity & employee safety
- Fire resistant vinyl construction is self-extinguishing
- Smooth surface design allows user to comfortably enter & exit

## CORE PRODUCT DATA

| ASSEMBLED WEIGHT | ASSEMBLED SIZE | SHIP WEIGHT |
|---|---|---|
| 168 lbs | 96" W x 0.16" L x 96" H | 208 lbs |
| **PACKAGE 1 SIZE** | **COLOR / FINISH** | **FREIGHT TYPE** |
| 30" W x 96" D x 32" H | Clear | LTL Palletized |

**AVAILABILITY** Available

**QUICKSHIP: --**

Products are sold through Vestil distributor partners. Contact a distributor for current pricing and ordering.

## PRODUCT SPECIFICATIONS

| | |
|---|---|
| **Mounting Design** | Header |
| **Overlap Style** | Standard |
| **PVC/Vinyl Thickness (in.)** | 0.16 |
| **Strip Width (in.)** | 16 |
| **Opening Width (in.)** | 96 |
| **Opening Height (in.)** | 96 |
| **Tensile Strength (PSI)** | 2635 |
| **Maximum Tensile Elongation (percent)** | 388 |
| **Graves Tear Load (lb.)** | 35.4 |
| **Graves Tear Extension (in.)** | 2.07 |
| **Load at 100% Elongation (lbs.)** | 32.2 |
| **Strength at 100% Elongation (PSI)** | 1181 |
| **Stiffness in Flexure - 23 degrees Celsius (PSI)** | 1805 |
| **Brittleness Temperature by Impact (degrees Cels** | .35 |
| **Recommended Operating Temperature - Range (** | -10 to 140 |
| **Specific Gravity** | 1.22 |
| **Haze Transmittance (percent)** | 6.30 |
| **Luminous Transmittance (percent)** | 82.80 |

## PRODUCT & SHIPPING REFERENCE

Shipping Point: **Angola, IN 46703**

Warranty: **90 Days**

**AVAILABLE PRODUCT RESOURCES**

**SCAN FOR CURRENT PRODUCT DATA**

Live product page: https://www.vestil.com/product.php?FID=27